


**FIBROELAST®-Round rod**

2531.4.

**Material:**Polyester-based polyurethane
Hardness 70 Shore A**Colour:**

white

Physical properties:

Shore hardness A: 70

100% modulus of elasticity: 3,0 [N/mm²]300% modulus of elasticity: 6,0 [N/mm²]Tensile strength: 28 [N/mm²]

Elongation: 500 [%]

Tear resistance: 58 [kN/m]

Permanent set (70°C): 45 [%]

Rebound elasticity: 55 [%]

Maximum deformation: 40 [%]

2531.4. FIBROELAST®-Round rod

Order No	d ₁	l ₁
2531.4.016	16	330
2531.4.020	20	500
2531.4.025	25	500
2531.4.032	32	500
2531.4.040	40	500
2531.4.050	50	500
2531.4.063	63	500
2531.4.080	80	500
2531.4.100	100	500
2531.4.125	125	500